CHEMICAL RESISTANCE CHART FOR POLYEURO® 7502

The following chemical resistance data were obtained from a 70-75 mils film of POLYEURO® 7502 immersed in each chemical listed below at 70-75 degF for a period of 7 days. Like other industrial maintenance coatings, POLYEURO®7502 has chemical and temperature limitations. Please read the disclaimer below. For chemicals other than those listed below, proper testing must be completed prior to application of the coating system. It is advisable to consult your local Polycoat representative.

CHEMICAL SOLVENTS		CHEMICAL SOLVENTS	
Xylene	4	Motor Oil	2
Toluene	4	Gasoline (unleaded)	3
Acetone	4	Diesel	1
2 Methyl Butane	4	Brake Fluid	3
MTBE	4	Hydraulic Oil	3
Hexane	4	Methanol	3
ACIDS and BASES			
Sewage	3	Sulphuric Acid 60%	4
Hydrogen Sulphide gas (H ₂ S gas)	4	Sulphuric Acid 30%	4
Hydrocholric Acid 35%	4	Sulphuric Acid 10%	2
Hydrochloric Acid 10%	2	Sulphuric Acid 5%	2
Hydrochloric Acid 5%	2	Potassium Hydroxide 10%	1
Propylene Carbonate	3	Potassium Hydroxide 20%	2
Acetic Acid, 10%	2	Sodium Hydroxide 50%	2
Phosphoric Acid, 10%	2	Sodium Hydroxide 25%	1
Ammonium Hydroxide 10%	1	Sodium Hydroxide 10%	1
Ammonium Hydroxide 20%	2	Sodium Hydroxide 5%	1
Salt Water (10%)	1	10% Sugar/Water	1
Drinking Water	1	De-Ionized Water	1

CHART KEYS:

- 1: no visible damage
- 2: little visible damage
- 3: some effect swelling, discoloration, cracking
- 4: not recommended
- 5: satisfactory for splash, spillage and secondary containment (72-96 hours)

DISCLAIMER: All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. The is information relates to the specific material designated and may not be valid for such material used in combination with any other material or in any process. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use and usassumes all risk and liability resulting from his use of the product. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other thanhose contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer.

Test performance results were obtained in a controlled environment and POLYCOAT PRODUCTS makes no claim that these tests or synother tests, accurately represent all environments. Application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

PUBLISHED TECHNICAL DATA AND INSTRUCTIONS ARE SUBJECT TO CHANGE WITHOUT NOTICE. CONTACT YOUR LOCAL POLYCOAT PRODUCTS REPRESENTATIVE FOR CURRENT TECHNICAL DATA AND INSTRUCTIONS.



POLYCOAT PRODUCTS

A Division of American Polymers Corp.

(562) 802-8834 **TEL** (562) 921-7363

14722 Spring Avenue, Santa Fe Springs, CA 90670-5108 USA INTERNET● www.polycoatusa.com E-MAIL● sales@polycoatusa.com

POLYEURO® 7502 CHEMICAL RESISTANT