



REVISION 04/12/08

### Product Description

Quick-N-Cure is a single component, proprietary, liquid catalyst that reduces the cold weather cure time of aromatic polyurethane polyurea coatings. Quick-N-Cure may be used to speed the cure of Polyglaze AR, AR-SF, PC-220, PC-220SF, PC-220OF, PC-440, PC-440SF, PC-440SC, Poly-I-Gard® 246, Poly-I-Gard® 246SF, Poly-I-Gard® 246OF, Poly-I-Gard® 246SC.

### FEATURES

- » Quick-N-Cure may be used to accelerate cure time in cold weather applications

### TYPICAL USES

- » Vertical Surfaces
- » When Quick Access is Necessary
- » Creates a Caulking Compound for Plywood Joints, Cracks, Concrete Expansion Joints and Flashings

### PACKAGING

**0.7 ounce (20 gram) vial**

**1 quart (0.95 liter) can**

### Color

Red

### Mixing

Maximum mixing ratio: 0.2 to 0.6 ounces Quick-N-Cure to 1 gallon Aromatic Coating (5.9cc to 17.7cc Quick-N-Cure to 3.78 liters Aromatic Coating).

- OR -

1 to 3 ounces Quick-N-Cure to 5 gallons Aromatic Coating (29.6cc to 88.7cc Quick-N-Cure to 18.9 liters Aromatic Coating).

The amount of catalyst to be added should be determined based on job conditions. However, it is recommended that not more than 0.1% to 0.2% of Quick-N-Cure be added (by weight) to the coating.

Mix Quick-N-Cure into the coating by using a mechanical mixer. Mix Quick-N-Cure into the coating until a homogeneous mixture and color is achieved. Do not mix in an up and down motion.

The pot life of the resulting compound will be approximately 4-6 hours. This time will vary based on temperature, humidity and amount of Quick-N-Cure used.

### Cleanup

Quick-N-Cure has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored

### TECHNICAL DATA (BASED ON DRAW DOWN FILM)

<b>Pot Life at 75°F (24°C), 50% R.H.</b>	4-6 hours
<b>Minimum Mixing ratio Quick-N-Cure: Aromatic Coating</b>	0.6 oz/1 gal 10cc/3.37 liters
<b>Specific Gravity</b>	1.008
<b>Total Solids by Weight, ASTM D-2369</b>	100%
<b>Total Solids by Volume, ASTM D-2697</b>	100%
<b>Viscosity at 75°F (24°C)</b>	100 ± 50 cps
<b>Volatile Organic Compounds, ASTM D-2369-81</b>	0 lb/gal 0 gm/liter

indoors at a temperature between 60-95°F (15-35°C).

### Storage

Quick-N-Cure has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

### Limitations

For use in cold temperatures only. Excessive Quick-N-Cure will result in a reduction of the physical properties of the base membrane.

Adding excessive amounts of Quick-N-Cure may result in foaming. Containers that have been opened must be used as soon as possible. Do not dilute under any circumstance.

### Warning

**This product contains Curatives.**



**Disclaimer:** All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments. © 2018 Polycoat Products. All rights reserved.

