



POLYCOAT PRODUCTS

A Division of American Polymers Corp.

POLY-CAULK® PX27 SL

100% Solids Self-Leveling Polyurethane Joint Sealant

Technical Data Sheet

DESCRIPTION

Poly-Caulk® PX27 Self Leveling is a two component, 1:1 (A:B) ratio by volume, 100% solids polyurethane sealant.

FEATURES

- ❖ Odorless
- ❖ Flexible
- ❖ 100% Solids Meets VOC Regulations
- ❖ Cured Material Remains Flexible, Even In Cold Temperatures

TYPICAL USES

Poly-Caulk® PX27 SL is used on interior and exterior horizontal concrete surfaces, to repair random cracks, control joints, and other areas where down time is limited.

- ❖ Airports
- ❖ Spalls
- ❖ Saw/Utility Cuts
- ❖ Industrial/Manufacturing Facilities
- ❖ Bridge Headers
- ❖ Truck Aprons
- ❖ Parking Garage Decks

COLORS

Concrete Grey

PACKAGING

1.5 gallon kit: One 1gallon can, net fill 0.75 gallons of Side-A and One 2 gallon pail, net fill 0.75 gallons of Side-B.

COVERAGERATESLF/Gallon

		Width of Joint						
		¼"	⅜"	½"	⅝"	¾"	⅞"	1"
Depth of Joint	¼"	308	205	154	123	102	88	77
	⅜"	205	136	102	82	68	58	51
	½"	154	102	77	61	51	44	38
	⅝"	123	82	61	49	41	35	30
	¾"	102	68	51	41	34	29	25
	⅞"	88	58	44	36	29	25	22
	1"	77	51	38	30	25	22	19

Coverages and yields shown do not include allowances for loss or waste and variations in job conditions. Each user must establish their own factors for loss from experience.

TECHNICAL DATA

Mixing Ratio (A:B) by volume	1:1 (A:B)
Specific Gravity	
Part-A	1.02
Part-B	1.44
Viscosity at 80 °F	
Part-A	65 ± 10 poise
Part-B	70 ± 10 poise
Pot Life @ 77°F (25°C)	2-3 hours
Tackfree Time @ 77°F (25°C)	12 hours
Cure Time @ 75°F, R.H. 50%	36-48 hours
Shore A hardness, ASTM D-2240	30 ± 5A
Tensile Strength, ASTM D-412	300 ± 50 psi
Elongation, ASTM D-412	800 ± 50%
Tear Strength, ASTM D-624	50 ± 5 pli
Solids Content	100%

SURFACE PREPARATION

Allow concrete to cure 28 days before installation.

All joints must be clean and dry prior to installing Poly-Caulk® PX27 SL.

If joint is damp, dry with heat torch.

Remove all dust from the concrete pores prior to installing Poly-Caulk® PX27 SL.

Backer rod should be used in control joints, the recommended depth is not greater than 25% of the total depth of the slab.

Construction joints are to be filled to full depth using no backer rod or silica sand.

To repair T-joints, the joint should be cut a minimum of 25% of the total depth of the slab. The side of the T-joint must be cut 1½" from the joint and a minimum of ½" deep.

For random crack and spall repairs, each side of the crack should be cut to create a minimum ½" deep vertical edge.

Ensure that all joint edges are at 90° angles to grade with no V-grooving or feather edges.

All surfaces must be primed with Polyprime 2180 or Polyprime EBF.

MIXING

Poly-Caulk® PX27 SL may not be diluted under any circumstance.

Pre-mix Poly-Caulk® PX27 SL Side-B material before combining with Side-A. Side-A material requires no mixing.

Add Side-A to Side-B while mixing, using a mechanical mixer at low speed. Mix until a homogeneous mixture and color is obtained (at least 5 minutes). Use care to scrape the sides of the container to ensure that no unmixed material remains.

Use caution not to whip air into the material as this may result in pinhole blisters and/or shortened pot life.

APPLICATION

Apply using a caulking gun, hand pressure-type or pour from container.

This material can be applied at ambient temperatures from 40°F (4.4°C) to as high as 135°F (57°C).

The product needs to be conditioned at 75-80°F prior to use.

FINISHING

After applying Poly-Caulk® PX27 SL, wait 36-48 hours, depending on temperature and humidity before opening to traffic.

CLEANUP

Cured product may be disposed of without restriction. Mix excess A and B material and allow to cure. Check local, state and federal laws before disposing of material.

STORAGE

Poly-Caulk® PX27 SL should be stored at room temperature, 60-90°F (15-35°C).

Poly-Caulk® PX27 SL has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers.

LIMITATIONS

Discoloration will occur if exposed to UV, however no change will occur in the physical properties.

WARNING

This product contains Isocyanates and Curatives.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data and instructions.

LIMITED WARRANTY

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products current published physical properties. Polycoat Products warrants that its products, when properly installed by a state licensed waterproofing contractor according to Polycoat Products guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of one (1) year. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments.