



POLYCOAT PRODUCTS

A Division of American Polymers Corp.

POLYCOAT-STAINGARD 6000

*Aliphatic Polyaspartic
Polyurea Topcoat
Technical Data Sheet*

DESCRIPTION

Polycoat-Staingard 6000 is a 100% solids by volume, aliphatic polyaspartic coating, two-component, liquid applied, environmentally friendly surface topcoat for waterproofing membrane systems. Polycoat-Staingard 6000 is quick curing and specifically formulated to be installed in thin film applications.

FEATURES

- ❖ Quick Cure
- ❖ High Tensile Strength
- ❖ Abrasion Resistant
- ❖ Topcoat over aromatic polyurea, polyurethane and epoxy applications ranging from 35°F to 130°F, service temperature 0°F to 200°F
- ❖ Very Durable
- ❖ Excellent Weatherability
- ❖ Seamless Waterproofing Membrane
- ❖ UV Resistant For Superior Gloss Retention
- ❖ Meets California AQMD Requirements
- ❖ Color Stable
- ❖ High Gloss

TYPICAL USES

- ❖ Concrete
- ❖ Plywood
- ❖ Cold Storage Areas
- ❖ Industrial Warehouses
- ❖ Chemical Plants
- ❖ Off-Shore Oil Platforms
- ❖ Steel
- ❖ Plastic
- ❖ Food Processing Areas
- ❖ Pulp and Paper Mills
- ❖ Fertilizer Plants
- ❖ Pipeline Barges

COLOR

Clear, Grey and Tan

Custom colors are also available. Minimum order of 100 gallons (378.5 liters). See color chart for special provisions. Contact Polycoat Products for more information.

PACKAGING

2 gallon kit (7.57 liter): 1 gallon (3.79 liters) can part-A and 1 gallon (3.79 liters) can Part-B.

10 gallon kit is not an in stock item and is available with advanced notice. Contact Polycoat Products for availability.

MIXING

Polycoat-Staingard 6000 may not be diluted under any circumstance. Proportions are premeasured. Polycoat-Staingard 6000 Part-A and Part-B should be mixed individually before combining. Add Part-B to Part-A while mixing, using a mechanical mixer at medium speed. Mix until a homogeneous mixture and color is obtained (at least 5 minutes) and mix frequently during application to maintain uniform color. Use care to scrape the sides of the container to ensure that no unmixed material remains. Use caution not to whip air into the material as this may result in pinhole blisters and/or shortened pot life.

TECHNICAL DATA, POLYCOAT-STAINGARD 6000, CLEAR

Coverage Rate	See Guide
	Specification
Dry Film Thickness, exclusive of aggregate, two coats	
@ ½ gal/100 sq. ft. each	16 mils 406 microns
Pot Life at 75°F (24°C), 50% RH	20-30 minutes
Hardness, ASTM D-2240	65 ± 2 Shore D
Tear Resistance, Die C, ASTM D-624	400 ± 50 pli 70 ± 10 kN/m
Tensile Strength, ASTM D-412	3000± 200psi 20.7 ± 2 MPa
Ultimate Elongation, ASTM D-412	70 ± 10%
Specific Gravity,	
Side-A	1.1
Side-B	1.05
Total Solids by Weight, ASTM D-2369	100%
Total Solids by Volume, ASTM D-2697	100%
Viscosity at 75°F (24°C),	
Side-A	2600 ± 300cps
Side-B	1100 ± 300cps
Volatile Organic Compounds, ASTM D-2369-81	0 lb/gal 0 gm/liter

TECHNICAL DATA, POLYCOAT-STAINGARD 6000, PIGMENTED

Coverage Rate	See Guide
	Specification
Dry Film Thickness, exclusive of aggregate, two coats	
@ ½ gal/100 sq. ft. each	16 mils 406 micron
Pot Life at 75°F (24°C), 50% RH	20-30 minutes
Hardness, ASTM D-2240	65 ± 2 Shore D
Tear Resistance, Die C, ASTM D-624	375 ± 50 pli 65.6 ± 10 kN/m
Tensile Strength, ASTM D-412	2600± 200psi 17.9 ± 2 MPa
Ultimate Elongation, ASTM D-412	30 ± 10%
Specific Gravity,	
Side-A	1.1
Side-B	1.24
Total Solids by Weight, ASTM D-2369	100%
Total Solids by Volume, ASTM D-2697	100%
Viscosity at 75°F (24°C),	
Side-A	2600 ± 300cps
Side-B	2000 ± 300cps
Volatile Organic Compounds, ASTM D-2369-81	0 lb/gal 0 gm/liter

Do not mix any material that cannot be used within 20-30 minutes.

APPLICATION

Polycoat-Staingard 6000 can be applied by phenolic resin core roller, high pressure spray, or through a cup gun under low pressure. Polycoat-Staingard 6000 should be applied at a minimum film thickness of 5 mils. It should be noted that the heavier the application, the longer the curing process takes.

Apply Polycoat-Staingard 6000 evenly over the entire deck. For best results, use an airless sprayer. A phenolic resin core roller may be used, but extra care should be taken not to cause air bubbles.

CURING

At 70°F (21°C) and 50% relative humidity, allow each coat to cure 3-4 hours.

Allow 6 hours before permitting light pedestrian traffic and at least 24-48 hours before permitting heavy pedestrian traffic on to the finished surface.

Uncured Polycoat-Staingard 6000 is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in batch sizes and thickness of application.

Low temperature and/or low humidity extend the cure time.

EQUIPMENT CLEANUP

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

STORAGE

Polycoat-Staingard 6000 has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers.

LIMITATIONS

Surfaces must be dry, clean and free of foreign matter .

Clear coating may turn opaque and cloudy due to moisture penetration, especially in exterior applications.

Surface may be slippery when wet.

Containers that have been opened must be used as soon as possible.

Do not dilute under any circumstance.

WARNING

This product contains Isocyanates.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data and instructions.

LIMITED WARRANTY

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products current published physical properties. Polycoat Products warrants that its products, when properly installed by a state licensed waterproofer contractor according to Polycoat Products guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of one (1) year. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner that infringes on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, and nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments.