


Concrete Substrate (properly prepared substrate)



Plywood Substrate (properly prepared substrate)

Features	Typical Usage
<ul style="list-style-type: none"> • Chemical Resistance • Elastomeric • Environmentally Safe • Excellent Low Temperature • Flexible • Good Thermal Stability • Meets USDA Criteria • Non-Gassing • Rapid Setting and Cure Times • Seamless • Solvent Free 	<ul style="list-style-type: none"> • Balconies • Patios • Sun Decks • Walkways

Technical Data

Pedestrian Traffic Deck Coating System 36 & 58 Dry Mil (914 microns and 1143 microns)

Primer Polyprime® EBF-LV
Polyprime® 21

Basecoat PC-260

Topcoat Poly-I-Gard™ 295

Packaging

Polyprime® EBF-LV
2-gallon kit: One 1 gallon (3.78 liters) can of Side-A and One 1 gallon (3.78 liters) can of Side-B or
10-gallon kit: One 5 gallon (18.9 liters) pail of Side-A and One 5 gallon (18.9 liters) pail of Side-B

Polyprime® 21
3-gallon kit: One 3.5 gallon pail, net fill 2 gallons (7.57 liters) of Side-A and One 1 gallon (3.78 liter) can of Side-B or
15-gallon kit: Two 5 gallon (18.9 liter) pails of Side-A and One 5 gallon (18.9 liter) pail of Side-B

PC-260
 One 1 gallon can, net fill 0.8 gallons (3 liters) of Side-A and One quart can, net fill 0.2 gallons (0.78 liters) of Side-B or
5-gallon kit: One 5 gallon pail, net fill 4 gallons (15.12 liters) of Side-A and One 1 gallon (3.78 liters) can of Side-B

Poly-I-Gard™ 295
4.4-gallon kit: One 5-gallon pail, net fill 4-gallons (15.12 liters) of Side-A, and one 1/2-gallon, net fill 0.4 gallon (1.514 liters) jar of Side-B

Primers, base and topcoats have a shelf life of 1 year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Description

The Polydeck® 555 Pedestrian Traffic Deck System is a very fast setting, rapid curing, high solids, polyurethane/polyurea, liquid applied, chemically cured, rapid return-to-service waterproofing coating system. The system utilizes a two-component epoxy primer, a two-component, non-gassing, thermal stable, elastomeric basecoat, and a two-component, solvent free, hybrid aliphatic polyurea topcoat.

The Polydeck® 555 Pedestrian Traffic Deck System is a user friendly, low-odor coating system that is specifically designed to be tough and durable enough to withstand light to heavy pedestrian traffic. It is a high elongation elastomeric system which properties allow it to expand and contract with normal structural movements. It can be applied to protect surfaces against spalling, freeze/thaw damage, and chemicals commonly encountered on pedestrian decks. It will neither soften in heat nor embrittle in the cold. Recommended system coverage mil thickness: light pedestrian traffic systems, 36 dry mils (944 dry microns) and heavy pedestrian traffic systems 48 dry mils (1219 dry microns). Make sure to use the correct grade of product which complies with VOC regulations/requirements applicable as per federal, state, statutory, counties, cities and local bodies at the place of installation.

Product Instructions

For complete information associated with the application of all Polycoat Products decking systems and products, refer to the General Guidelines and Technical Data Sheets of the Polycoat Products catalog, which describes the products, surface preparation, job conditions, finishing details and other necessary information.

Coatings Application

PHASE 1:

Check area of application to ensure that it conforms to the substrate requirements, as stated in the General Guidelines. Prime all joints, cracks, flashings with approved primers as specified below in Phase 2. Apply PC-260 over all joints, cracks and flashing. Do not mix more material than can be used in 20 minutes. Bridge the joints, cracks, and flashings with 4" (10.2 cm) Straight Jacket Tape, pushing it into the paste with a trowel. Over Straight Jacket Tape, apply a stripe coat of the PC-260 and taper it onto the adjacent surface. Allow the surface to cure for 6 to 8 hours.

PHASE 2:

Substrates other than new plywood are to be primed. Primer is optional for new plywood. Metal and concrete which have been cleaned should be primed with Polyprime® 21 at a rate of 1 gallon/300 sqft (0.14 liters/sqm) or 300 sqft/gallon. Apply using a brush or phenolic core roller. This will result in a minimum 4 dry mils (102 microns) thick membrane.

Note: For rough or porous concrete or when outgassing is a concern, use Polyprime® EBF-LV at an approximate rate of 1 gallon/200 sqft (0.21 liters/sqm) or 200 sqft/gallon; this rate may vary on the porosity of the substrate. Allow primer to become tack free before moving to the Coating Application. The point at which the primer is deemed

tack free is when the primer passes thumbprint test. The thumbprint test is defined by when a thumbprint is left in the primer and primer does not transfer to the thumb. If the primer has been allowed to remain tack free for more than 12 hours, it is necessary to solvent wipe surface with VOC-compliant solvent and re-prime the surface.

PHASE 3:

Apply PC-260 to substrate at a rate of 1 1/2 gallons/100 sqft (0.62 liters/sqm) or 66 sqft/gallon. For best results, use a 1/8" (0.32 cm) notched trowel or notched squeegee. A 3/8" (0.965 cm) nap phenolic core roller may be used, but extra care should be taken to prevent air bubbles. Spread mixed PC-260 evenly over the entire deck resulting in a minimum of 22 dry mils (559 ± 51 microns) thick membrane. Allow PC-260 to cure before proceeding to phase 4.

Note: Polycoat basecoats should be applied the same day as the primer to avoid missing the primer recoat window. If this is not possible, broadcast heavy with aggregate into the primer to aid in the adhesion of the basecoat to the primer. Do not exceed recoat window of 12 hours after cure and if recoat window is passed, then solvent wipe the surface with VOC-compliant solvent and re-prime before proceeding with the next coat/phase.

PHASE 4:

For light pedestrian traffic, apply Poly-I-Gard® 295 at a rate of 1 1/2 gallon/100 sqft (0.62 liters/sqm) or 66 sqft/gallon. Immediately broadcast and backroll washed, dry, rounded sand, 20 mesh (0.841 mm), 6.5+ Mohs minimum hardness at a rate of 10-15 lbs/100 sqft (0.50-0.75 kgs/sqm), into the wet second coat, covering it completely. This coat will result in an additional minimum 12 ± 2 dry mils (304 ± 51 microns) thick membrane, exclusive of aggregate. After this coat has cured, remove all loose aggregate.

PHASE 5:

For heavy pedestrian traffic, apply Poly-I-Gard® 295 at a rate of 3/4 gallon/100 sqft (0.31 liters/sqm) or 120 sqft/gallon. Immediately broadcast and backroll washed, dry, rounded sand, 20 mesh (0.841 mm), 6.5+ Mohs minimum hardness at a rate of 10-15 lbs/100 sqft (0.50-0.75 kgs/sqm), into the wet second coat, covering it completely. This coat will result in an additional minimum 24 ± 2 dry mils (610 ± 51 microns) thick membrane, exclusive of aggregate. After this coat has cured, remove all loose aggregate.

FINISHED SYSTEM

When applied as directed above, the Polydeck® 555 Pedestrian Traffic Deck System will provide minimum 36 to 48 dry mils ± 5 (914 to 1143 ± 125 dry microns), exclusive of aggregate, of superior waterproofing protection. Requires a continuous coating application to minimize lines and/or streaking. Any optional adhesion test is to be performed seven days after product application.

Limitations

The following conditions must not be coated with Polycoat Products deck coating systems or products: on grade slabs, split slabs with buried membrane, sandwich slabs with insulation, slabs over unvented metal pan, magnesite, or concrete with a structural integrity less than 3000 psi. Asphalt



surfaces and asphalt overlays may be coated with Polycoat decking systems if first coated with the Polycoat™ PC-IM 129.

Concrete must exhibit 3000 psi minimum strength. Concrete surfaces to be coated must be trowel finished in compliance with the American Concrete Institute (except that hand troweling is not required), followed by a fine-haired brooming, left free of loose particles, and shall be without ridges, projections, voids and concrete droppings that would be mechanically detrimental to coating application or function.

New concrete must be cured for 28 days (see General Guidelines). Polycoat Products coating systems should not be subjected to rising water tables or hydrostatic pressure on slab-on-grade decks. The only acceptable grade of plywood is APA rated exterior grade or better. The appearance and physical characteristics of the plywood and grade should be considered. Plywood should be new or cleaned and sanded (see General Guidelines). The coating should be applied at least 5°F (3°C) above the dew point.

Coverage rates recommended are based on lab conditions, applied at 75°F (24°C) ambient temperature and are intended to be minimum coverage rates on clean, smooth plywood, and are exclusive of additional amounts needed to fill potholes, spalling, scaling, rough and irregular surfaces. Porosity and roughness of the substrate, aggregate size, and product temperature will affect coverage rates. Material mil thickness rates are calculated on theoretical coverage for a smooth substrate and do not account for the actual texture or substrate conditions in the field or at the time of application. Sample mockups on the projects are recommended to determine the exact coverage rates necessary to waterproof the deck to acceptable standards.

Equipment should be cleaned with a urethane grade environmentally safe solvent, as permitted under local regulations, immediately after use. Uncured materials are sensitive to heat and moisture. The substrate must be structurally sound and sloped for proper drainage. Polycoat Products assumes no liability for substrate defects. Field visits by Polycoat Products personnel are for the purpose of making technical recommendations only and are not to supervise or provide quality control on the job site.

Warning

The products in this system contain Isocyanates, Solvents, Epoxy Resin, and Curatives.



Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proved to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors.

© 2024 Polycoat Products. All rights reserved. Revision 20241021.AG

