

Product Description

Polyglaze™ Hardener is a single component, low viscosity, accelerating agent. This accelerator enhances the moisture curing characteristics of all grades of Polyglaze™ coatings and all grades of the Poly-I-Gard® 246 coatings. Please select the correct Product Grade which comply with VOC regulations as per Federal, State, Statutory Bodies, County and City Regulations/Codes at the place of installation of product.

Features

- Fast Cure Time
- Saves in Labor Cost – Apply Two Coats in One Day

Typical Uses

- Creates a Caulking Compound for Plywood Joints, Cracks, Concrete Expansion Joints and Flashings
- Vertical Surfaces
- When Quick Access is Necessary

Packaging

1 quart (0.95 liter) can

Color

Clear (Pale Yellow)

Mixing

Polyglaze™ Hardener may be mixed into all grades of Polyglaze™ and all grades of Poly-I-Gard® 246 surface protection coatings by using a mechanical mixer. Mix Polyglaze™ Hardener into the topcoat until a homogeneous mixture and color is attained. Do not mix in an up and down motion.

VOLUME MIXING RATIO:

0.5 pint Polyglaze™ Hardener to 1 gallon Polyglaze/Poly-I-Gard® 246 (0.24 liters Polyglaze™ Hardener to 3.78 liters Polyglaze™/Poly-I-Gard® 246).

- OR -

1 Quart Polyglaze™ Hardener to 5 gallons Polyglaze™/Poly-I-Gard® 246 (0.95 liters Polyglaze™ Hardener to 18.9 liters Polyglaze™/Poly-I-Gard® 246).

The pot life of the resulting compound is approximately 1-3 hours at 75°F (24°C) and 50% relative humidity.

Cleanup

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

Technical Data (Based on Draw Down Film)

Pot Life at 75°F (24°C), 50% R.H. (during application) 1-3 hours

Volume Mixing Ratio, Polyglaze™ Hardener: Polyglaze™ / Poly-I-Gard® 1:20

Specific Gravity 0.87

Viscosity at 75°F (24°C) 100 ± 50 cps

Storage

Polyglaze™ Hardener has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Limitations

Not recommended for indoor applications. Should be used in well-ventilated areas due to its strong odor. Containers that have been opened must be used within 1-3 hours. Polyglaze™ Hardener may react with atmospheric moisture and render it unusable. Do not dilute under any circumstance.

Not for use with Poly-I-Gard® 295 or Poly-I-Gard® 295OF.

Warning

This product contains Curatives.

This product is considered Dangerous Goods. DOT regulations classify it as: UN 1760, CORROSIVE LIQUID N.O.S., (Contains Amine), Class 8, PG III.



Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2020 Polycoat Products. All rights reserved. Revision 20200403.EA

