



Product Description

Polyeuro® MPL 80 is a two component, 1:1, 100% solids, fast set, liquid applied, modified polyurea liner system for metal, concrete, fiberglass and wood surfaces.

Features

- Abrasion and Impact Resistant
- Chemical Resistance
- High Build
- Low Shrinkage
- Low Temperature Flexibility
- Quick Drying
- Seamless
- Tough and Elastomeric

Typical Uses

- Boat Linings
- Cargo Holds
- Cargo Liners
- Containment Areas
- Encapsulation of Fiberglass Bodies and Polystyrene Foams
- Horse Trailers
- Industrial Floors
- Truck-Bed Surfaces
- Utility Vehicles
- Walkways
- Waterproof Decking

Packaging

10-gallon kit	5 gallons (18.9 liters) Side-A and 5 gallons (18.9 liters) Side-B.
100-gallon kit	50 gallons (189 liters) Side-A and 50 gallons (189 liters) Side-B .

Colors

Neutral, Grey, Black. Custom colors are available upon request.

Mixing

Polyeuro MPL 80 may not be diluted under any circumstances. Thoroughly mix Polyeuro MPL 80 Side-B Base material with air driven power equipment until a homogeneous mixture and color is obtained.

Side-B base material must be thoroughly agitated until a homogenous mixture is obtained. Do not allow air to be incorporated into the product. Total suspension must be achieved. Side-A Isocyanate requires no mixing

Coverage

Polyeuro MPL 80 may be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mil (0.254 microns) thickness is one gallon per 1600 sqft (3.78 liters per 149 sqm).

Estimating Formula: (1600 sqft per gal /Dry Mil Thickness) x Solids Content = Application Rate per gallon.

Technical Data (Based on Draw Down Film)

Mix Ratio by Volume	1A : 1B
Pot Life @ 150°F (65.5°C), 50% R.H.	3-5-Seconds
Tack-Free Time (150 mils thickness)	20-40 Seconds
Recoat Time	0 - 12 hours
Viscosity at 150-160°F (65.5-71°C)	
Side-A	120 ± 20 cps
Side-B	60 ± 20 cps
Density (Side-A & Side-B Combined)	9.0 lbs/gal
Flash Point	> 200°F (93.3°C)
Hardness, ASTM D2240	80 ± 5 Shore A
Tensile Strength, ASTM D412*	2000 ± 300 psi 13.79 ± 2.07 MPa
Elongation, ASTM D412*	300% ± 25%
Tear Resistance, ASTM D412*	300 ± 50 pli 52.45 ± 8.8 kNm
Service Temperature (Dry)	-20°F to 250°F -28.89°C to 121°C

*These physical properties from sample sprayed with Graco Foam Cat 200 @ 2000 psi minimum, with Gusmer GX7-400 mechanical purge gun @ 150-160°F (65°C to 71°C). Different machine and parameter will change these properties. User should perform their own independent testing as properties are approximate.

Surface Preparation

In general, coating performance and adhesion are directly proportional to surface preparation. All surfaces must be free of oil, grease, dirt and other contaminants.

PICK-UP TRUCK

Sanding and scuffing of the original paint finish is required to obtain a permanent bond of the spray-on liner to the pick-up truck bed.

After the vehicle is masked with paper and the surface has been thoroughly cleaned, sand the surface using 40 grit sanding discs on an autobody disc arbor.

In areas which cannot be accessed by power tools, surface preparation can be completed by hand using 80 or 100 grit sandpaper or a coarse scuffing pad such as Scotchbrite.


Take care that all edges at tape lines are well scuffed and sanded.

After sanding and scuffing the surface must be clean and dust free.

CONCRETE

Remove all contaminants such as oil, grease, dirt, form oil residue, wax, laitance or any other chemical product prior to proceeding with surface preparation. The surface should be free of voids, pot holes or bug holes, loose or weak concrete and the necessary surface profile must be achieved and have open textured surface by blast cleaning or equivalent mechanical means as listed below to ensure proper adhesion and good surface appearance.

Abrasive blast using brush blast technique or better to achieve a desired surface texture (CSP 4-5 per ICRI Guidelines).



Vacuum to remove dust, etc., prior to application of primer.

Use fiberglass (C-Veil Glass) or a geotextile cloth to bridge cracks over the primed surface.

Primer is always recommended to take care of voids, pot holes or bug holes etc.

Application

Both Side-A and Side-B materials should be preconditioned at 75-80°F (24-27°C) before application.

Polyeuro® MPL 80 should be applied using a plural component, heated, high pressure 1:1 spray mixing equipment like Graco's Hydra Cat, Gusmer or other equivalent machine may be used.

Both Side-A and Side-B materials should be sprayed at temperatures above 150°F (65°C). Adequate pressure and temperature should be maintained at all times.

Storage

Polyeuro® MPL 80 has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Side-A and Side-B drums are recommended to be stored above 60°F (15°C). Avoid freezing temperatures.

Store drums on wooden pallets to avoid direct contact with the ground. If stored for a long period of time, rotate Side-A and Side-B drums regularly.

Limitations

Due to its aromatic composition, Polyeuro® MPL 80 will tend to yellow or darken in color after exposure to UV light. Polyeuro MPL 80 may be topcoated with an aliphatic polyurethane coating, such as Polycoat's Polyglaze® 100, AL-50, or Staingard® 7000 polyaspartic, for a color-fast glossy finish.

Do not open until ready to use.

Both Side-A and Side-B containers must be fitted with a desiccant device during use.

Warning

This product contains Isocyanates and Curative Material.

Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2020 Polycoat Products. All rights reserved. Revision 20201125.AG