



**Product Description**

Polyeuro® MPL 85 Aluminum is a two component, 1:1, 100% solids, fast set, liquid applied, modified polyurea liner system for metal, concrete, fiberglass and wood surface.

**Features**

- Abrasion and Impact Resistant
- Chemical Resistance
- High Build
- Low Temperature Flexibility
- Quick Drying
- Seamless
- Tough and Elastomeric

**Typical Uses**

- Abrasion Resistance Over Wood, Metal and Concrete.
- Chemical Resistance for Styrofoam Flotation
- Secondary-Containment Coating- Which Provides a Chemical Resistant Membrane Over Concrete and Steel in Approved Tank Farms
- Water and Chemical Resistance for Concrete Block and Poured Walls
- Waterproofing for Urethane Foam Roofing

**Packaging**

- 10-gallon kit**      One 5 gallon pail of Side-A and one 5 gallon pail of Side-B
- 100-gallon kit**      One 50 gallon drum of Side-A and one 50 gallon drum of Side-B

**Color**

Aluminum

Due to its aromatic composition, Polyeuro® MPL 85 Aluminum will tend to yellow or darken in color and will become flat after exposure to UV light. Polyeuro® MPL 85 Aluminum may be topcoated within twelve hours of application with an aliphatic polyurethane/polyurea coating for a colorfast finish.

**Coverage**

Polyeuro® MPL 85 Aluminum may be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mil (0.254 microns) thickness is one gallon per 1600 sqft (3.78 liters per 149 sqm).

Estimating Formula: (1600 sqft per gal /Dry Mil Thickness) x Solids Content = Application Rate per gallon.

**Mixing**

Polyeuro® MPL 85 Aluminum may not be diluted under any circumstances. Thoroughly mix Polyeuro® MPL 85 Aluminum Side-B with air driven power equipment until a homogeneous mixture and color is obtained.

**Surface Preparation**

In general, coating performance and adhesion are directly proportional to surface preparation. Most failures in the

**Technical Data (Based on Draw Down Film)**

<b>Mix Ratio by Volume</b>	1A : 1B
<b>Pot Life @ 150-160°F</b>	3 - 5 seconds
<b>Tack Free Time (150 mils)</b>	20 -40 seconds
<b>Recoat Time</b>	0 - 12 hours
<b>Viscosity at 77-80°F (25°C), Brookfield</b>	
<b>Side-A</b>	600 ± 100 cps
<b>Side-B</b>	750 ± 100 cps
<b>Density (Side-A &amp; Side-B Combined)</b>	9.22 lbs/gal
<b>Flash Point</b>	> 200°F (93.3°C)
<b>Hardness, ASTM D2240</b>	85 ± 5 Shore A
<b>Tensile Strength, ASTM D412*</b>	2500 ± 200 psi 17.71 ± 1.37 MPa
<b>Elongation, ASTM D412*</b>	300 ± 20%
<b>Tear, ASTM D624*</b>	225 ± 25 pli 39.35 ± 4.4 kNm
<b>Service Temperature</b>	-40°F to 250°F -40°C to 121°C

\*These physical properties from sample sprayed with Graco Foam Cat 200 @ 2000 psi minimum, with Gusmer GX7-400 mechanical purge gun @ 150-160°F (65°C to 71°C). Different machine and parameter will change these properties. User should perform their own independent testing as properties are approximate.

performance of surface coatings can be attributed to poor surface preparation. Polyurea coatings rely on the structural strength of the substrate to which they are applied. All surfaces must be free of dust, dirt, oil, grease, rust, corrosion and other contaminants. When coating substrates previously used, it is important to consider the possibility of substrate absorption, which may affect the adhesion of the coating system, regardless of the surface preparation. Polycoat recognizes the potential for unique substrates from one project to another. The following information is for general reference, and for project-specific questions, contact Polycoat.

**Application**

Both Side-A and Side-B materials should be preconditioned to 75-80°F (24-27°C) before application.

Recommended surface temperature must be at least 5°F (3°C) above the dew point.

Polyeuro® MPL 85 Aluminum should be applied using a plural component, heated, high pressure 1:1 spray mixing equipment like Graco's Reactor, Glass Craft or other equivalent machine may be used.

Both Side-A and Side-B materials should be sprayed at a minimum of 2000 psi and at temperatures above 150°F (65°C). Adequate pressure and temperature should be maintained at all times.

Polyeuro® MPL 85 Aluminum should be sprayed in smooth, multidirectional passes to improve uniform thickness and appearance.

**Storage**

Polyeuro® MPL 85 Aluminum has a shelf life of six (6) months from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-



35°C).

Side-A and Side-B drums are recommended to be stored above 60°F (15°C). Avoid freezing temperatures.

Store drums on wooden pallets to avoid direct contact with the ground. If stored for a long period of time, rotate Side-A and Side-B drums regularly.

### Limitations

Do not open until ready to use.

Both Side-A and Side-B containers must be fitted with a desiccant device during use.

### WARNING

**This product contains Isocyanates and Curative Material.**

**Limited Warranty:** Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

**Disclaimer:** All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2020 Polycoat Products. All rights reserved. Revision 20201125.AG