



Product Description

Polyeuro® LP-1188 is a two component, 1:1.88, 100% solids, fast set, liquid applied, modified polyurea liner system for metal, concrete, fiberglass, and wood surfaces.

FEATURES

- » Seamless
- » Tough and Elastomeric
- » High Build
- » Quick Drying
- » Chemical Resistance
- » Low Temperature Flexibility
- » Abrasion and Impact Resistant
- » Low Pressure Application

TYPICAL USES

- » Truck Bed Surfaces
- » Utility Vehicles
- » Cargo Liners
- » Boat Linings
- » Cargo Holds
- » Waterproof Decking
- » Horse Trailers
- » Walkways
- » Mold Castings
- » Encapsulation of Fiberglass Bodies

PACKAGING

One 55 gallon drum net content 500 lbs. of Side-A (Isocyanate side) and two 55 gallon drum net content 450 lbs. each drum of Side-B (Resin side)

Colors

Clear/Neutral or Black. Custom colors are available upon request. Color packs, when used, must be added to Part-B.

Due to its aromatic composition, Polyeuro® LP-1188 will tend to yellow or darken in color after exposure to UV light. Polyeuro® LP-1188 may be topcoated within twelve hours of application with an aliphatic polyurethane/polyurea coat-ing for a colorfast finish.

Coverage

Polyeuro® LP-1188 may be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mil thickness is one gallon per 1600 sq. ft.

Surface Preparation

In general, coating performance and adhesion are directly proportional to surface preparation. Most failures in the performance of surface coatings can be attributed to poor surface preparation. Polyurea coatings rely on the structural strength of the substrate to which they are applied. All surfaces must be free of dust, dirt, oil, grease, rust, corrosion and other contaminants. When coating substrates previously used, it is important to consider the possibility of substrate absorption, which may affect the adhesion of the coating system, regardless of the surface preparation. Polycoat recognizes the potential for unique substrates from one project

TECHNICAL DATA (BASED ON DRAW DOWN FILM)

Mix Ratio by Volume	1A : 1.88B
Pot Life @ 80°F (26°C)	12-16-Seconds
Tack Free Time (150 mils thickness)	40-60 Seconds
Recoat Time	6 - 12 hours
Viscosity at 80°F (26°C), Brookfield	
Side-A	700-900 cps
Side-B	700-900 cps
Density (Side A & B Combined)	9.2 lbs/gal
Flash Point	> 200°F (93.3°C)
Hardness, ASTM D-2240	91-93 Shore A
Tensile Strength, ASTM D-412*	1300 ± 200 psi 8.96 ± 1.38 MPa
Elongation, ASTM D-412*	250% ± 50%
Tear Resistance, ASTM D-412*	175 ± 25 pli 30.6 ± 4.37 kNm
Service Temperature Dry	-20°F to 200°F

NOTE: Above physicals are from lab drawn films. Actual spray physicals may vary.

to another. The following information is for general reference, and for project-specific questions, contact Polycoat.

NEW AND OLD CONCRETE:

Refer to SSPC-SP13/NACE 6, or ICRI 03732: CSP 3-5. New concrete must be cured for 28 days prior to product application. Surface must be clean, dry, sound and offer sufficient profile for product adhesion. Remove all dust, dirt, oil, form release agents, curing compounds, salts, efflorescence, laitance and other foreign matter by shotblasting and/or suitable chemical means, in accordance with local chemical regulations. Rinse thoroughly, to achieve a pH between 8.0 and 11.0. Allow to dry completely. If old concrete has a surface that has deteriorated to an unacceptably rough surface, Polycoat Products PC-260 or a mixture of Polyprime 21 and sand should be used as a repair agent for cracks, spalls, bug holes and voids. Upon full cure of the repair agent, prime the entire surface intended for coating..

CONCRETE SURFACE PREPARATION REFERENCE:


- ASTM D4258 - Standard practice for cleaning concrete
- ASTM D4259 - Standard practice for abrading concrete
- ASTM D4260 - Standard practice for etching concrete
- ASTM F1869 - Standard test method for measuring moisture vapor emission rate of concrete
- ICRI 03732 - Concrete surface preparation

WOOD:

All wood should be clean, dry and free of any knots, splinters, oil, grease or other contaminants. Splintered or rough areas should be sanded. Knots should be repaired using Polycoat Products PC-260 with sand. Upon full cure of the repair agent, prime the entire surface intended for coating.

STEEL (ATMOSPHERIC AND IMMERSION EXPOSURE):

Remove all oil, grease, weld spatters and round off any sharp edges from surface. Minimum surface preparation is Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Opti-mum



surface profile is 3-4 mils. Prime and shoot Polyeuro® on to any bare metal the same day as it is cleaned to minimize any potential flash rusting.

ALUMINUM:

Aluminum should be blasted with aluminum oxide or sand, and not with steel or metal grit. Excessive blasting may result in a warped or deformed surface. After blasting, wash aluminum with a commercially available aluminum cleaner. Allow to dry, then prime.

BRASS AND COPPER:

Brass and copper should be blasted with sand, and not with steel or metal grit. Remove all dust and grease prior to applying primer.

GALVANIZED SURFACES:

Clean and degrease any contaminated surfaces before priming. Do not blast galvanized surfaces with an abrasive grit. An adhesion test is recommended prior to starting the project.

FIBERGLASS REINFORCED PLASTIC:

The gel coat should be lightly blasted or sanded with 80 grit sandpaper and cleaned.

PLASTIC FOAMS:

Enhanced adhesion is obtained when the foam is mechanically abraded. When coating polystyrene, do not use a solvent-based primer.

TEXTILES, CANVAS, FABRICS:

Adhesion to most fabrics, geothermal membranes and textiles does not require a primer.

STAINLESS STEEL:

Stainless steel may be grit blasted and degreased before priming. Some stainless steel alloys are so inert that it is not possible to achieve a satisfactory bond. An adhesion test is recommended prior to starting the project.

NEW AND OLD CAST IRON:

Blast with a steel grit and degrease before priming. Old cast iron is difficult to prepare for a satisfactory bond. It can absorb oil and water soluble contaminants that will keep returning to the surface after the coating system has been applied and affect the coating system adhesion. An adhesion test is recommended prior to starting the project.

ALL OTHER SURFACES:

An adhesion test is recommended prior to starting the project.

Mixing

Polyeuro® LP-1188 may not be diluted under any circumstances. Thoroughly mix Polyeuro® LP-1188 Part-B (Resin side) with air driven power equipment until a homogeneous mixture and color is obtained..

Application

Both Side-A and Side-B materials should be preconditioned to 75-80°F before application.

Recommended surface temperature must be at least 5°F above the dew point.

Polyeuro® LP-1188 should be applied using plural component,

low pressure spray mixing equipment. The simple spray equipment can have a single motor driving two separate fixed ratio proportioning pumps. Side-A and Side-B are pumped separately to a static mixing tube for air assisted or airless spray. It is recommended to use a x 24 element mixing wand/Static spiral mixer for proper mixing.

Contact Polycoat Products for further information.

Storage

Polyeuro® LP-1188 has a shelf life of six (6) months from date of manufacture in original, factory sealed containers.

Avoid exposure to freezing temperatures.

Store drums on wooden pallets to avoid direct contact with the ground.

If stored for a long period of time, rotate Side-A and Side-B drums regularly.

Limitations

Do not open until ready to use.

Both Side-A and Side-B containers must be fitted with a desiccant device during use.

Warning

This product contains Isocyanates and Curative Material.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments. © 2019 Polycoat Products. All rights reserved. **REV-20190304AA**