

Product Description

Polyeuro® 1050H has NSF-61 approval for direct contact with potable water, and is recommended for use as a coating or lining on suitably primed carbon steel, non-ferrous metal and concrete. Polyeuro® 1050H offers a tack-free time of less than five minutes and exhibits 20-30% elongation upon curing with 65 Shore D hardness.

Features

- 100% Solids
- Abrasion and Impact Resistant
- Chemical Resistant
- High Build, Quick Dry
- Horizontal Surface Application
- Low Temperature Flexibility
- Plural Component Spray Application

Typical Uses

- Canals, Dams & Basins
- Concrete/Steel
- Food Processing Facilities
- Lakes, Ponds and Water Containment
- Leach Tanks
- Man Holes
- Mining
- Pen Stocks
- Petrochemical Plants
- Pipelines Coating (Internal)
- Power Plants
- Pulp and Paper Plants
- Secondary Containment
- Water and Wastewater Treatment Plants
- Water-Storage Tanks

Typical Systems

CARBON STEEL

Primer: Polyprime 3042
Finish: Polyeuro® 1050H

CONCRETE

Primer: Polyprime 3042
Finish: Polyeuro® 1050H
Refer to Specification Guide for further detail.

Packaging

160-gallon kit One 55 Gallon Drum, containing 53.4 gallons (202.1 liters) of Side-A and two 55 Gallon Drums of Side-B, each containing 53.4 (202.1 liters) gallons

Colors

Off-white with a medium sheen gloss.

Coverage

Polyeuro® 8245 may be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mil (0.254 microns) thickness is one gallon per 1600 sqft (3.78 liters per 149 sqm).

Technical Data (Based on Draw Down Film)

Mix Ratio by Volume	1A : 2B
Solids Content	100%
Gel Time, 100 ± 10°F (-12.2°C)	40-80 seconds
Tack-Free Time @ 70°F (21°C), 40mils	max 5 minutes
Service Time @ 70°F (21°C)	24-48 hours
Viscosity at 100°F (32°C), ASTM D445-79:	
Side-A	125 ± 50 cps
Side-B	500 ± 50 cps
Specific Gravity, ASTM D4659:	
Part-A	1.2 max
Part-B	1.05 max
Flash Point	> 200°F (93.3°C)
Hardness, ASTM D2240	65 ± 5 Shore D
Dry Film Thickness per Coat	20-100 mils
VOC Content, ASTM D412	0 gm/l
Tensile Strength, ASTM D412	2800 ± 200 psi 19.042 ± 1.37 MPa
Elongation, ASTM D412	25 ± 10%
Tear, Die C, ASTM D624	400 ± 50 pli 69.9 ± 8.8 kNm
Sag Resistance	Excellent
Dry Time @ 70°F (21°C): to touch	20 minutes
Dry Time @ 70°F (21°C): for light foot traffic	1 hour
Dry Time @ 70°F (21°C): for heavy foot traffic	24 hours
Cured to Service	24 hours
Maximum Recoat Period	24 hours
Full Cure	120 hours
Surface Temperature Resistance	
Immersion	120°F (49°C)
Dry	180°F (82°C)
Humidity Tolerance on Application	<85%
Material Temperature Required for Application:	
Activator	95 to 105°F (35 to 40°C)
Base	95 to 120°F (35 to 49°C)
Allowable Ambient Air Temp for Application	
Maximum	120°F (49°C)
Minimum	25°F (-3.9°C)

Estimating Formula: (1600 sqft per gal /Dry Mil Thickness) x Solids Content = Application Rate per gallon.

Mixing

Polyeuro® 1050H may not be diluted under any circumstances. Use appropriate cleaner for purge line and flushing of equipment and if spraying stops for periods exceeding the pot life of the material. Thoroughly mix Polyeuro® 1050H Side-B material with air driven power equipment until a homogeneous mixture and color is obtained. Opened material must be used within 1-2 days due to moisture sensitivity. Side-B must be thoroughly agitated for at least thirty (30)

minutes prior to application. Total suspension must be achieved. Side-A requires no mixing.

Surface Preparation

In general, coating performance and adhesion are directly proportional to surface preparation. Most failures in the performance of surface coatings can be attributed to poor surface preparation. Polyurea coatings rely on the structural strength of the substrate to which they are applied. All surfaces must be free of dust, dirt, oil, grease, rust, corrosion and other contaminants. When coating previously used substrates, it is important to consider the possibility of substrate absorption, which may affect the adhesion of the coating system, regardless of the surface preparation. Polycoat recognizes the potential for unique substrates from one project to another. The following information is for general reference. For project-specific questions, contact Polycoat.

NEW AND OLD CONCRETE

Refer to SSPC-SP13/NACE 6, or ICRI 03732: CSP 3-5. New concrete must be cured for 28 days prior to product application. Surface must be clean, dry, sound and offer sufficient profile for product adhesion. Remove all dust, dirt, oil, form release agents, curing compounds, salts, efflorescence, laitance and other foreign matter by shotblasting and/or suitable chemical means, in accordance with local chemical regulations. Rinse thoroughly to achieve a pH between 8.0 and 11.0. Allow to dry completely. If old concrete has a surface that has deteriorated to an unacceptably rough surface, Polycoat Products PC-260 or a mixture of Polyprime 21 and sand should be used as a repair agent for cracks, spalls, bug holes and voids. Upon full cure of the repair agent, prime the entire surface intended for coating.

CONCRETE SURFACE PREPARATION REFERENCE

ASTM D4258 - Standard practice for cleaning concrete.
ASTM D4259 - Standard practice for abrading concrete.
ASTM D4260 - Standard practice for etching concrete.
ASTM F1869 - Standard test method for measuring moisture vapor emission rate of concrete.
ICRI 03732 - Concrete surface preparation.

WOOD

All wood should be clean, dry and free of any knots, splinters, oil, grease or other contaminants. Splintered or rough areas should be sanded. Knots should be repaired using Polycoat Products PC-260 with sand. Upon full cure of the repair agent, prime the entire surface intended for coating.

STEEL (ATMOSPHERIC AND IMMERSION EXPOSURE)

Remove all oil, grease, weld spatters and round off any sharp edges from surface. Minimum surface preparation is Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Optimum surface profile is 3-4 mils. Prime and shoot Polyeuro® onto any bare metal the same day as it is cleaned to minimize any potential flash rusting.

GALVANIZED SURFACES

Clean and degrease any contaminated surfaces before priming. Do not blast galvanized surfaces with an abrasive grit. An adhesion test is recommended prior to starting the project.

FIBERGLASS REINFORCED PLASTIC

The gel coat should be lightly blasted or sanded with 80 grit sandpaper and cleaned.

PLASTIC FOAMS

Enhanced adhesion is obtained when the foam is mechanically abraded. When coating polystyrene, do not use a solvent-based primer.

TEXTILES, CANVAS, FABRICS

Adhesion to most fabrics, geothermal membranes and textiles does not require a primer.

STAINLESS STEEL

Stainless steel may be grit blasted and degreased before priming. Contact Polycoat Products for recommended primer. Some stainless steel alloys are so inert that it is not possible to achieve a satisfactory bond. An adhesion test is recommended prior to starting the project.

ALUMINUM

Aluminum should be blasted with aluminum oxide or sand, and not with steel or metal grit. Excessive blasting may result in a warped or deformed surface. After blasting, wash aluminum with a commercially available aluminum cleaner. Allow to dry, then prime. Contact Polycoat Products for recommended primer.

NEW AND OLD CAST IRON

Blast with a steel grit and degrease before priming. Old cast iron is difficult to prepare for a satisfactory bond. It can absorb oil and water soluble contaminants that will keep returning to the surface after the coating system has been applied and affect the coating system adhesion. An adhesion test is recommended prior to starting the project.

ALL OTHER SURFACES

An adhesion test is recommended prior to starting the project.

Application

Apply over prepared or suitably primed carbon steel or concrete. Application temperature for Polyeuro® 1050H should be between 40-120°F (4.4-40°C) with relative humidity of <85%. Do not apply product unless temperature is at least 5° (3°C) above the dew point. Recoat schedule is 1-3 hours dependent upon environment.

Application Methods

Check area of application to ensure that it conforms to the substrate requirements.

Use Graco "Hydra-Cat" 45:1 Airless equipment or equal designed for heated, plural-component, high pressure spray application. High pressure equipment should have the capacity to apply product to a maximum 2500 psi from the proportioner to meet job site conditions. Heat and maintain material temperature in a range of 95-110°F (35-43°C) and utilize insulated material hoses and application equipment to ensure spray consistency, metering and degree of cure of properly mixed product. Band heaters should not be used to heat or maintain temperature.

The conditioned materials shall be supplied to the proportioning equipment at a flowable, pumpable viscosity, and in such volume delivery to assure full supply for each pump stroke. Recirculation system and solvent purge equipment is necessary to keep material maintained and spray equipment clean during application stoppage and/or for periods when exceeding the product potlife.

Equipment Cleanup

Equipment should be cleaned with an environmentally safe, urethane-grade solvent (alcohol free) as permitted under local regulations immediately after use

Storage

Polyeuro® 1050H has a shelf life of one (1) year year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Side-A and Side-B drums are recommended to be stored



**POLYCOAT
PRODUCTS**

A Division of American Polymers Corp.

TECHNICAL DATA SHEET

POLYEURO® 1050H

Polyurea Polyurethane Copolymer Protective Coating

above 60°F (15°C). Avoid freezing temperatures.

Store drums on wooden pallets to avoid direct contact with the ground. If stored for a long period of time, rotate Side-A and Side-B drums regularly

Limitations

Polyeuro 1050H® is not recommended for prolonged exposure to concentrated acids.

Do not open until ready to use.

No liability is assumed by Polycoat Products for substrate defects and/or improper substrate preparation and application.

Warning

This product contains Isocyanates and Curative Material.

Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2020 Polycoat Products. All rights reserved. Revision 20201125.AG