



Product Description

PipePro Ultra is a direct-to-metal, quick-set, two component, 100% solids polyurethane designed to protect pipelines from corrosion and abrasion. It is especially formulated for **Water Transmission Piping** and **Piping ID/OD** applications.

PipePro Ultra is a high performance 100% solids structural polyurethane which is designed specifically for steel, ductile iron, and concrete pipe. Persistent adhesion and high impact resistance allows it to be utilized in the severest environments.

Approvals

Meets the requirements of AWWA C222-18.

Certified to NSF/ANSI Standard 61 by NSF for lining portable water tanks, pipes, valves, and fittings

Pipes > 4"; Valves and Fittings > 4"; Tanks > 1000 gallons (3785 liter): thickness of 20-120 mils (508-3048 microns)

Features

- 1:1 Mix Ratio
- Abrasion and Impact Resistant
- Excellent adhesion directly to steel and ductile iron
- Fast Curing for increased productivity and short turn-around time
- High Tensile Strength
- Horizontal Surface Application
- Low Temperature Flexibility
- Plural Component Spray Application
- Quick Gel Time
- Unlimited film build with single multi-pass application (25 to 35 mils for most steel applications)
- Zero VOC (100% Solids)

Typical Uses

- Buried Tank Exteriors
- Penstocks
- Piping ID/OD
- Power Plants
- Steel Pilings
- Steel Pipeline Exteriors
- Steel Pipe Linings and Repair
- Steel Poles (above & below ground)
- Storage Tanks
- Water Transmission Piping

Packaging

10-gallon pail kit	5 gallons (18.9 liters) Side-A and 5 gallons (18.9 liters) Side-B
100-gallon drum kit	50 gallons (189 liters) Side-A and 50 gallons (189 liters) Side-B
540-gallon tote kit	270 gallons (1022 liters) Side-A and 50 gallons (1022 liters) Side-B

Technical Data (Based on Draw Down Film)

Initial Setting Time @70°F (20°C)	<5 minutes (set time may be adjusted depending on production needs)
Curing Time Before Handling @70°F (20°C)	5-20 minutes
Ultimate Cure @70°F (20°C)	< 7 days
Recoat Time (Temp/Thickness Dependent) @70°F (20°C)	1 – 3 hours
% Solids Content by Volume	100%
Theoretical Coverage	1604 sqft/US gal/mil (1000 sqm/liter/micron)
Adhesion to Steel, ASTM D4541	> 1,500 psi
Hardness, ASTM D2240 Shore D	80 ± 3 Shore D
Flexibility, ASTM D522	No Cracking or Delamination - 2" Mandrel
Abrasion Resistance (CS17, 1000 grams weight, 1000 revolutions), ASTM D4060	74 mg
Resistance to Cathodic Disbondment, ASTM G95-07(13)	< 8 mm average results
Chemical Resistance, ASTM D543	< 5% Change in mass, length and width (10% Sulfuric Acid, 30% Sodium Chloride, 30% Sodium Hydroxide, No.2 Diesel Fuel)
Dielectric Strength, ASTM D149	769 volts per mil
Volatile Organic Compounds, (Side-A & B combined) ASTM D2369-81	0 lbs/gal 0 gm/liter
Impact Resistance, ASTM G14	125.8 in. lbs.
Accelerated Weathering, ASTM G154	No Cracking; some chalking & darkening
Water Absorption, ASTM D570	1.33 %
Tear Strength, ASTM D624	450 ± 50 pli 78.9 ± 8.8 kN/m
Tensile Strength, ASTM D412	5000 ± 500 psi 34.5 ± 3.4 MPa
Elongation ASTM D412	5% ± 2%

Colors

Blue, black, grey, and white.

Coverage

PipePro Ultra may be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mil (0.254 microns) thickness is one gallon per 1600 sqft (3.78 liters per 149 sqm).

Estimating Formula: (1600 sqft per gal /Dry Mil Thickness) x Solids Content = Application Rate per gallon.

Surface Preparation

Ensure the surface is clean, dry and uncontaminated in accordance with SSPC-SP1. Continue only if the substrate temperature is more than 5°F (3°C) above the dew point

temperature during surface preparation and coating application.

Abrasive blast clean with angular media (sand, aluminum oxide, garnet or steel grit G40 or coarser). DO NOT USE steel shot or non-angular products or slag-based media.

Steel Surfaces: blast to a Near White Blast (SSPC-SP10; NACE 2; SA 2.5):

minimum 3 - 4 mil (75 – 100 microns) profile for immersion; buried pipe and tanks.

minimum 2.0 mil (50 microns) profile for atmospheric service.

Ductile Iron Surfaces: abrasive blast to achieve a surface anchor profile of 2-5 mils or greater. Remove all rust and loose oxides.

Concrete Surfaces: abrasive blast to remove any surface laitance.

Galvanized Steel Surfaces: contact a Polycoat representative. See Polycoat Application Instructions for additional details.

For project-specific questions, contact Polycoat.

Mixing

PipePro Ultra may NOT be diluted under any circumstances. Agitate individual components thoroughly before use to disperse pigments and assure homogeneity. DO NOT thin or mix Side-A and Side-B together.

Application

Spray apply PipePro Ultra using a plural component, 1:1 mix ratio, heated airless spray unit.

See below for suggested application settings and conditions:

Condition	Material	Surface	Ambient	Humidity
Optimum	130-140°F (54-60°C)	70-90°F (21-32°C)	70-90°F (21-32°C)	0-50%
Minimum	125°F (53°C)	40°F (4°C)	35°F (2°C)	0%
Maximum	140°F (60°C)	140°F (60°C)	120°F (49°C)	85%

Surface should be clean, dry, and more than 5°F (3°C) above the dew point.

High film thickness can be obtained in one continuous coating operation, using one of several techniques. Contact a Polycoat representative for more details.

For coating on a conveyor line, a uniform pipe temperature of between 70°F (20°C) and 120°F (55°C) to enable the coating to cure quickly.

A second coat may be applied over the first, so long as it is applied within the recoat window. Otherwise, it will be necessary to roughen the surface to ensure good intercoat adhesion. Contact your Polycoat representative for details on recoating windows.

Cure

Condition	Dry to Touch (75°F)	Dry to Handle (75°F)
Quick-Set	50-60 seconds	4-5 minutes
Medium-Set	70-90 seconds	6-9 minutes
Slow-Set	2.5-3 minutes	13-15 minutes

Storage

PipePro Ultra has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 50-79.9°F (10-26.6°C). Please keep the ISO from freezing when shipping and storing.

This material will react with humidity and moisture. Keep containers tightly sealed and in dry conditions. For clean-up, use MEK or 50/50 MEK/Xylene.

Limitations

Provide ample ventilation in confined areas. Protect skin by wearing rubber gloves, safety goggles and other appropriate PPE. Wear NIOSH approved cartridge type face mask and fresh air respirator in the spray area. Review Application Guidelines for additional information and consult with your Polycoat representative for additional safety information.

Warning

This product contains Isocyanates and Curative Material.

Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2023 Polycoat Products. All rights reserved. Revision 20230807.JC