



Product Description

Poly-Caulk® PX27SL (Self-Leveling) is a two component, 1:1 (A:B) ratio by volume, 100% solids polyurethane sealant.

Features

- 100% Solids
- Cured Material Remains Flexible, Even in Cold Temperatures
- Flexible
- Odorless

Typical Uses

Poly-Caulk® PX27SL is used on interior and exterior horizontal concrete surfaces, to repair random cracks, control joints, and other areas where down time is limited.

- Airports
- Bridge Headers
- Industrial and Manufacturing Facilities
- Parking Garage Decks
- Saw/Utility Cuts
- Spalls
- Truck Aprons

Packaging

1.5-gallon kit One 1 quart (0.98 liter) can of Side-A and One 2 gallon pail, net fill 1.25 gallons (4.73 liters) of Side-B

Color

Concrete Grey

Coverage

Coverages and yields shown do not include allowances for loss or waste and variations in job conditions. Each user must establish their own factors for loss from experience.

Surface Preparation

Allow concrete to cure 28 days before installation.

All joints must be clean and dry prior to installing Poly-Caulk® PX27SL. If joint is damp, dry with heat torch.

Remove all dust from the concrete pores prior to installing Poly-Caulk® PX27SL.

Backer rod should be used in control joints, the recommended depth is not greater than 25% of the total depth of the slab.

Construction joints are to be filled to full depth using no backer rod or silica sand.

To repair T-joints, the joint should be cut a minimum of 25% of the total depth of the slab. The side of the T-joint must be cut 12" (20.4 cm) from the joint and a minimum of 2" (5.08 cm) deep.

For random crack and spall repairs, each side of the crack should be cut to create a minimum 2" (5.08 cm) deep vertical edge.

Ensure that all joint edges are at 90° angles to grade with no

Technical Data (Based on Draw Down Film)

Mix Ratio by Volume	1A : 1B
Specific Gravity, Side-A	1.03 ± 0.1
Side-B	1.41 ± 0.1
Viscosity at 75°F (24°C) Side-A	50 ± 20 poise
Side-B	50 ± 20 poise
Pot Life at 75°F (24°C), 50% R.H.	25 ± 5 minutes
Tack Free Time at 77°F (25°C), 50% R.H.	12-24 hours
Cure Time at 75°F (24°C), 50% R.H.	36-48 hours
Hardness, ASTM D2240	30 ± 5 Shore A
Tensile Strength, ASTM D412	300 ± 50 psi 2.1 ± 0.3 MPa
Elongation, ASTM D412	800 ± 50%
Tear Strength, ASTM D624	50 ± 5 pli 8.8 ± 0.8 kNm
Total Solids by Weight, ASTM D2369	100%
Total Solids by Volume, ASTM D2697	100%
Volatile Organic Component	0 lb/gal 0 gm/liter

Depth of Joint	Width of Joint						
	1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"
1/4"	308	205	154	123	102	88	77
3/8"	205	136	102	82	68	58	51
1/2"	154	102	77	61	51	44	38
5/8"	123	82	61	49	41	35	30
3/4"	102	68	51	41	34	29	25
7/8"	88	58	44	36	29	25	22
1"	77	51	38	30	25	22	19



V-grooving or feather edges.

All surfaces must be primed with Polyprime® 2180 or Polyprime® EBF-LV.

Mixing

Poly-Caulk® PX27SL may not be diluted under any circumstance.

Pre-mix Poly-Caulk® PX27SL Side-B material before combining with Side-A. Side-A material requires no mixing. Add Side-A to Side-B while mixing, using a mechanical mixer at low speed. Mix until a homogeneous mixture and color is attained (at least 5 minutes).

Use care to scrape the sides of the container to ensure that no unmixed material remains.

Use caution not to whip air into the material as this may result in pinhole blisters and/or shortened pot life.

Do not mix in an up and down motion.

Application

Apply using a caulking gun, hand pressure-type or pour from container.

This material can be applied at ambient temperatures from 40°F (4.4°C) to as high as 135°F (57°C).

The product needs to be conditioned at 75-80°F (24-27°C) prior to use.

Finishing

After applying Poly-Caulk® PX27SL, wait 36-48 hours, depending on temperature and humidity before opening to traffic.

Cleanup

Cured product may be disposed of without restriction. Mix excess Side-A with Side-B material and allow to cure. Check local, state and federal laws before disposing of material.

Storage

Poly-Caulk® PX27SL should be stored at room temperature, 60-95°F (15-35°C).

Poly-Caulk® PX27SL has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Limitations

Discoloration will occur if exposed to UV, however no change will occur in the physical properties.

Warning

This product contains Isocyanates and Curatives.

Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2022 Polycoat Products. All rights reserved. Revision 20220412.AG