

PRODUCT DESCRIPTION

Poly-Fil LP is a two-component system consisting of a prepolymer (Side-A/ISO) and a polyol blend (Side-B/CAT)

Poly-Fil LP is excellent for applications requiring a wider footprint for flotation type tires that need a soft ride for the equipment and operator.

TYPICAL USES

- Farm and Agriculture Equipment
- Golf Course and Lawn Mowing Equipment
- Loaders at Transfer Stations (Adds Traction for Pushing as well as Flat-proofing)
- Skid Steers

PACKAGING

Tote kit: One tote of Side-A (2310 lbs 1060 kgs net), one tote of Side-B (2290 lbs, 1040 kgs net)

COLOR

Brownish Yellow Liquid

MIXING

When Poly-Fil LP Side-A and Poly-Fil Side-B are mixed, there is an exothermic reaction, therefore curing begins in the center of the mass. In the event that the temperature cannot be maintained at a constant 72°F (22°C) during the curing cycle, the curing time must be extended approximately eight (8) hours for every ten-degree temperature drop.

PREPARATION & APPLICATION

Before beginning each processing session, inspect equipment and verify that all the specified parts of the processing equipment are complete and in good working.

Read Safety Data Sheets (SDS) on Poly-Fil products before proceeding to flatproofing operation.

Please refer to the Polyfil Guide Specification Sheet for all information regarding processing, filling and installation procedures.

All standard procedures regularly practiced in the tire shop should be applied to the Poly-Fil operation, including tire mounting, equipment and material handling and clean up. A qualified tire serviceman will mount the tires.

STORAGE

Poly-Fil LP has a shelf life of twelve (12) months from date of manufacture, in factory-sealed containers.

Side-A and Side-B drums are recommended to be stored from 60-105°F (15-40°C). Keep in an indoor dry place, out of sunlight, tightly.

Avoid freezing temperatures.

Store drums on wooden pallets to avoid direct contact with the ground.

TECHNICAL DATA (BASED ON DRAW DOWN FILM)

Mix Ratio by Volume	1A:1B
Gel Time @ 80°F (26.6°C) (to achieve 10,000 cps)	150 ± 30 minutes
Cure Time (hours @ 90°F [32°C])	24-48 hours
Viscosity, cps @ 77° F (25° C)	
Side-A	600 ± 200
Side-B	500 ± 200
Specific Gravity @ 77°F (25°C)	
Side-A	1.046 ± 0.02
Side-B	1.037 ± 0.02
Hardness, Shore A	10 ± 2
Tensile Strength, ASTM D-412*	150 ± 25 psi (1.03 ± 0.2 MPa)
Elongation %, ASTM D-412*	275 ± 25
Tear Resilience (%), Die C	30 ± 5 pli (5.25 ± 0.9kN/m)
Total % Solids by Weight ASTM D-2369	100%
Total % Solids by Volume ASTM D-2397	100%
VOC	0 g/l

SAFETY

Use only in well ventilated areas. Avoid contact with skin. Wear chemical resistant gloves and proper safety equipment. If swallowed, call physician immediately. For eye contact, flush with water for 15 minutes and get medical attention. Refer to Safety Data Sheet (SDS) for details.

LIMITATIONS

Do not open until ready to use.

Both Side-A and Side-B containers must be fitted with a desiccant device during use.

WARNING

This product contains Isocyanates and Curative Material.



Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations. Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors.

© 2019 Polycoat Products. All rights reserved. Revision 20191104AG.

POLYCOAT PRODUCTS TEL 562.802.8834 | FAX 562.921.7363
info@polycoatusa.com | www.polycoatusa.com

