



Product Description

Poly-Caulk® JS-60 is a self-leveling, 100% solids, two-component modified polyurea-based elastomeric joint sealant. Poly-Caulk® JS-60 is a flexible material that is designed for 25% movement of an installed jointwidth. A minimum of 28 days is recommended for concrete to effectively cure prior to installing joint filler or joint sealant.

Features

- 100% Solids
- Cures from -20°F to 130°F (-29 to 54°C)
- Exceptional Elongation
- No Toxic Vapor, Odorless
- No VOCs
- Remains Flexible In Cold Temperatures
- Resists Jet Fuel
- USDA/FSIS Approved

Typical Uses

Poly-Caulk® JS-60 is designed to seal cracks, contraction joints, and control joints on new or old horizontal concrete surfaces. It can be applied on slabs where rapid turn around and return to use is needed because of how quickly the product cures. JS-60's memory capability allows for normal joint movement and accommodates slab movement where designed movement and thermal cycling will occur.

NOTE: Joints should be designed and prepared according to industry standards when using Poly-Caulk® JS-60. In order to achieve optimum movement, sealant depth should be ½ the sealant width—under no circumstances should the depth be greater than 1 inch in any joint.

- Industrial Facilities
- Sidewalks
- Roofing
- Parking Decks
- Bridge Decks
- Balcony Decks
- Water And Waste Water Treatment

Packaging

600-ml Cartridge: 300 ml Side-A 300ml Side-B packaged as a dual tube cartridge. Cartridges sold in cases of 4 or 10.

10-Gallon Kit: one 5 gallon (18.9 liter) pail of Side-A and one 5 gallon (18.9 liter) pail Side-B

Color

Concrete Grey

Coverage

The figures are estimated coverage rates and can vary on the joint conditions. The above numbers allow for 10% material waste due to overfilling.

Mixing

Poly-Caulk® JS-60 requires machine dispensing: use a 1:1 ratio pump with or without heater

Technical Data (Based on Draw Down Film)

Mix Ratio by Volume	1A : 1B
Specific Gravity, Side-A	1.08 ± 0.1
Side-B	1.01 ± 0.1
VOC	0%
Gel Time, ASTM D1640	2-3 minutes
Pot Life ASTM D1640	3-4 minutes
Tack Free Time, ASTM D1640 at 77°F (25°C), 50% R.H.	<5 minutes
Open to Foot Traffic, ASTM D1640	2 hours
Hardness, ASTM D2240	60 ± 5 Shore A
Tensile Strength, ASTM D638, Type IV	800 ± 50 psi 5.52 ± 0.3 MPa
Elongation, ASTM D638, Type IV	500 ± 50%
Tear Strength, ASTM D624	200 ± 25 pli 35 ± 4.4 kN/m
Tabor Abrasion, mg wt. loss (1000 g, 1000 revs, H-18) ASTM D4060	20-75
Total Solids by Weight, ASTM D2369	100%
Total Solids by Volume, ASTM D2697	100%

		Linear Feet Per Gallon			
		Width of Joint			
Depth of Joint		1/4"	1/2"	3/4"	1"
	1/4"	249	138	92	64
	1/2"	138	69	45	34
	3/4"	92	45	30	23
	1"	64	34	23	17

		Linear Feet Per 600 ml			
		Width of Joint			
Depth of Joint		1/4"	1/2"	3/4"	1"
	1/4"	32	24	16	11
	1/2"	24	11	8	6
	3/4"	16	8	5	3
	1"	11	6	3	2

The values stated in this technical data sheet are produced under controlled laboratory conditions.

Application

Performance and adhesion are directly related to preparation. Prior to installation the joint sidewalls must be freshly abraded with a clean-out saw equipment with a diamond blade and then vacuumed clean to exposing clean, dust free edges to maximize adhesion. For rough or broom finished concrete it is recommended to avoid overfilling the joint as shaving could be difficult. For smooth non-densified concrete, a stain prevention product / method should be considered to prevent etching.

Material Installation Temperature: 70°F or greater (21°C)

Exposure Temperature: -40°F to 200°F (-40°F to 93.3°C)

Cleanup

Cured product may be disposed of without restriction. Mix excess Side-A with Side-B material and allow to cure. Check local, state and federal laws before disposing of material.

Storage

Poly-Caulk® JS-60 should be stored at room temperature, 60-95°F (15-35°C).

Poly-Caulk® JS-60 has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Safety

For in-depth information on product safety and precautions, please review the product SDS sheets. Prior to using the product, ensure that you have the proper personal protection equipment (PPE) available. This includes but is not limited to the following items:

- Safety Glasses With a Splash Shield
- Minimum Organic Cartridge Respirator
- Rubber or Nitrile Gloves
- Disposable or Reusable Long Sleeve Overalls
- Rubber or Leather Boots

Always be sure to follow the precautions listed below when using the material:

- Do Not Use Near High Heat or Open Flame
- Do Not Take Internally
- Keep Out of Reach of Children

Limitations

Poly-Caulk® JS-60 should not be used to fill exterior cracks, control joints, or construction joints if deck or slab movement from thermal cycling is expected. This product is not recommended for use under non-breathing, resilient, or polymer flooring systems. Poly-Caulk® JS-60 is an aromatic-based polyurea. Discoloration from exposure to ultraviolet light may occur; however, the physical properties remain unaffected.

Warning

This product contains Isocyanates and Curatives.

Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2023 Polycoat Products. All rights reserved. Revision 20230807.JC