



### Product Description

Polyglaze® 100/100C/100SC is a polyester, aliphatic, single component, liquid applied, moisture cured, polyurethane topcoat for waterproofing membrane systems. Polycoat Products manufactures products in different VOC's ranging from 100 to 340 gms/liter to comply with VOC requirements in various regions. Make sure to use the correct grade of product which complies with VOC regulations/requirements applicable as per federal, state, statutory, counties, cities and local bodies at the place of installation.

### Features

- Durable
- Excellent Weatherability
- Limited Chemical Resistance
- Seamless Weatherproofing Membrane
- UV Resistant For Gloss Retention

### Typical Uses

- Concrete
- Heavy Pedestrian Traffic
- Most Metal, Wood or Masonry Surfaces
- Plywood
- Re-sealing Existing Polyurethane Surfaces

### Packaging

<b>1-Gallon</b>	1 gallon (3.78 liters) can
<b>5-Gallon</b>	5 gallon (18.9 liters) pail
<b>55-Gallon</b>	55 gallon drum, net fill 50 gallons (189 liters); Not a stock item

### Colors

**For Polyglaze® 100 (340 VOC):** Clear and Tan

**For Polyglaze® 100C (250 VOC):** Tan and Dolphin Grey. Tint-White with color packs are available in Stone Grey, Battleship Grey, Indian Sand, and Ash Brown.

**For Polyglaze® 100SC (100 VOC):** Tan, Dolphin Grey, Red and Tint-White. Tint-White with color packs are available in Stone Grey, Dolphin Grey, Battleship Grey, Tan, Indian Sand and Ash Brown.

Custom colors are also available. Minimum order of 250 gallons (945 liters). See color chart for special provisions.

When color packs are used the topcoat must be boxed for uniform color coverage. For pre-tinted standard color other than stock color, a minimum of 150 gallons (567 liters) is required.

### Coverage

The approximate coverage is 1 gallon/100 sqft (0.41 l/sqm). Coverage rate will depend on surface roughness and porosity.

### Technical Data (Based on Draw Down Film)

	<b>Polyglaze® 100 (340 VOC)</b>	<b>Polyglaze® 100C (250 VOC)</b>	<b>Polyglaze® 100SC (100 VOC)</b>
<b>Coverage Rate</b>	1 gal/100 sqft 0.41 l/sqm	1 gal/100 sqft 0.41 l/sqm	1 gal/100 sqft 0.41 l/sqm
<b>Dry Film Thickness per Coat</b>	10 ± 2 mils 254 ± 50 microns	11 ± 2 mils 279 ± 50 microns	12 ± 2 mils 305 ± 50 microns
<b>Hardness, ASTM D2240</b>	95 ± 5 Shore A	95 ± 5 Shore A	95 ± 5 Shore A
<b>Tear Resistance, Die C, ASTM D624</b>	450 ± 50 pli 78.8 ± 8.8 kN/m	450 ± 50 pli 78.8 ± 8.8 kN/m	500 ± 50 pli 87.6 ± 8.8 kN/m
<b>Tensile Strength, ASTM D412</b>	3800 ± 300 psi 26.2 ± 2.1 MPa	4000 ± 300 psi 27.6 ± 2.1 MPa	4000 ± 300 psi 27.6 ± 2.1 MPa
<b>Ultimate Elongation, ASTM D412</b>	250 ± 25%	250 ± 25%	250 ± 25%
<b>Specific Gravity</b>	1.14 ± 0.1	1.25 ± 0.1	1.31 ± 0.1
<b>Total Solids by Weight, ASTM D2369</b>	73 ± 2%	74 ± 2%	75.6 ± 2%
<b>Total Solids by Volume, ASTM D2697</b>	64 ± 2%	67 ± 2%	73.4 ± 2%
<b>Viscosity at 75°F (24°C)</b>	1200 ± 500 cps	1500 ± 500 cps	2000 ± 500 cps
<b>Volatile Organic Compounds, ASTM D2369-81</b>	2.79 lb/gal 334 gm/liters	2.09 lb/gal 250 gm/liters	0.82 lb/gal (with exempt solvent) 98 gm/liters

### Mixing

Before application, mix Polyglaze® 100/100C/100SC using a mechanical mixer at slow speed until a homogeneous mixture and color is attained. Use caution not to whip air into the material as this may result in pinhole blisters and/or shortened pot life. Do not mix in an up and down motion.

## Application

Apply Polyglaze® 100/100C/100SC evenly over the entire deck. For best results, airless sprayer or phenolic resin core roller may be used but extra care should be taken not to cause air bubbles.

Polyglaze® 100/100C/100SC may require more than one coat depending on the job specifications and requirements. When estimating material requirements, coverage rates tend to increase for subsequent coats of material. To achieve proper adhesion between coats it is imperative that recoating be done within 48 hours.

When Polyglaze® 100/100C/100SC Clear is used as a seal coat only, the surface must be clean, dry and primed with Polyprime® U to achieve proper adhesion to the surface. Polyprime® may discolor when used under Polyglaze® 100/100C/100SC Clear as a seal coat.

Requires a continuous coating application to minimize lines and/or streaking.

## Curing

At 75°F (24°C) and 50% relative humidity, allow each coat to cure 16 hours between each coat. Cure time will vary depending on temperature and humidity.

Allow 24 hours before permitting light pedestrian traffic and at least 72 hours before permitting heavy pedestrian or auto traffic on to the finished surface. If more than 48 hours passes between coats, re-prime the surface with Polyprime® U before proceeding.

If accelerated curing is required, add one quart (0.95 liter) of Polyglaze® Hardener in a 5 gallon pail (18.9 liters) of Polyglaze® 100/100C/100SC and mix thoroughly. This accelerated Polyglaze® 100/100C/100SC will cure in 6-8 hours at 75°F (24°C) and 50% relative humidity. The re-coat time with accelerator is reduced to 24 hours. If the re-coat window has passed, then solvent wipe the surface with VOC compliant solvent and re-prime surface with Polyprime® U before proceeding to the next coat.

## Cleanup

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

## Storage

Polyglaze® 100 has a shelf life of 1 year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

## Limitations

The following conditions must not be coated with Polycoat deck coatings or systems: split slabs, buried membrane, sandwich slabs with insulation, slabs over unvented metal pan, magnesite, and non-structural lightweight concrete. On grade slabs may receive Polycoat system coatings provided a moisture-vapor transmission test is first performed. Please contact Polycoat's technical department with the results.

With regard to coating asphalt surfaces, please contact Polycoat's technical department.

Surfaces must be dry, clean and free of foreign matter. Clear coating may turn opaque and cloudy due to moisture penetration, especially in exterior applications. Surface may be slippery when wet. Containers that have been opened must be used as soon as possible. Do not dilute under any circumstance.

## Warning

**This product contains Isocyanates and Solvent.**

**Polyglaze® 100/100C/100SC Clear is considered Dangerous Goods. DOT regulations classify it as: UN 1263, PAINT, Class 3, PG III, Flammable Liquid.**

**Limited Warranty:** Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

**Disclaimer:** All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2020 Polycoat Products. All rights reserved. Revision 20200917DM