

## Product Description

Poly-Caulk® HM (Hand-Mix) is a two component, modified aliphatic, rapid setting, self-leveling, 100% solids polyurea-caulking compound.

### Features

- 100% Solids
- Flexible
- Meets UDSA Criteria
- Remains Flexible, Even In Cold Temperatures

### Typical Uses

Poly-Caulk® HM is for small repairs on interior and exterior horizontal concrete surfaces, to repair random cracks, control joints, and other areas where down time is limited.

- Airports
- Bridge Headers
- Freezers & Cold Storage
- Grade Matching
- Industrial Facilities
- Manufacturing Facilities
- Parking Garage Decks
- Truck Aprons
- Warehouses
- Wastewater Treatment Plants

### Packaging

<b>1-Gallon kit</b>	One 1 gallon can (net fill 0.875 gallons or 3.31 liters) of Side-A and One 1 pint can (net fill 0.125 gallons or 0.47 liters) of Side-B
---------------------	-----------------------------------------------------------------------------------------------------------------------------------------

### Color

Gray

### Surface Preparation

Allow concrete to cure 28 days before installation.

Saw cut the joint to ACI Recommendations.

All joints must be clean and dry prior to installing Poly-Caulk® HM.

If joint is damp, dry with heat torch.

Remove all dust from the concrete pores prior to installing Poly-Caulk® HM.

Ensure that all joint edges are at 90° angles to grade with no V-grooving or feather edges.

### Mixing

Poly-Caulk® HM may not be diluted under any circumstance.

Pre-mix Poly-Caulk® HM Side-B material before combining with Side-A. Side-A material requires no mixing.

Add Side-A to Side-B while mixing, using a mechanical mixer at slow speed. Mix until a homogeneous mixture and color is

### Technical Data (Based on Draw Down Film)

<b>Mix Ratio by Volume</b>	7A : 1B
<b>Hardness, ASTM D2240</b>	80 ± 5 Shore A
<b>Tensile Strength, ASTM D412</b>	2000 ± 200 psi 13.8 ± 1.4 MPa
<b>Elongation, ASTM D412</b>	600 ± 50%
<b>Gel Time at 75°F (24°C), ASTM D2471</b>	4-5 minutes
<b>Tear Strength, ASTM D624</b>	425 ± 50 pli 74.5 ± 8.8 kN/m
<b>Total Solids by Weight, ASTM D2669</b>	100%
<b>Total Solids by Volume, ASTM D2697</b>	100%

attained (at least 5 minutes).

Use care to scrape the sides of the container to ensure that no unmixed material remains.

Use caution not to whip air into the material as this may result in pinhole blisters and/or shortened pot life.

Do not mix in an up and down motion.

### Application

Poly-Caulk® HM can be applied at ambient temperatures from 32°F (0°C) to as high as 135°F (57°C).

The product needs to be conditioned at 75-80°F (22-25°C) prior to use.

### Finishing

After applying Poly-Caulk® HM, wait 4-5 hours, depending on temperature and humidity before opening to traffic.

Slice off any over pour flush to grade.

### Cleanup

Cured product may be disposed of without restriction. Mix excess Side-A with Side-B material and allow to cure. Check local, state and federal laws before disposing of material.

### Storage

Poly-Caulk® HM should be stored at room temperature, 60-95°F (15-35°C).

Poly-Caulk® HM has a shelf life of 1 year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

### Limitations

Do not dilute Poly-Caulk® HM under any circumstances.

Do not use in cracks, construction joints or control joints if surface is subject to thermal cycling.

Discoloration will occur if exposed to UV, however no change will occur in the physical properties.

### Warning



This product contains Isocyanates and Curatives.

**Limited Warranty:** Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

**Disclaimer:** All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2020 Polycoat Products. All rights reserved. Revision 20200403.EA