

Product Description

Polycoat-Aquaseal™ 5000 is a single component, liquid applied, bitumen modified, coal tar free, moisture cured polyurethane waterproofing membrane. The standard Polycoat-Aquaseal™ 5000 may be applied to both fully cured concrete (28 days for poured in place and 10 days after grouting for block). Polycoat-Aquaseal™ 5000GC may be applied to Green Concrete. For Green Concrete, GC Additive must be added to Polycoat-Aquaseal™ 5000 at a ratio of ½ pint GC Additive (256 ml) to 5 gallons (18.9 liters) of Polycoat-Aquaseal™ 5000. Thoroughly mix with a variable speed drill and mixing paddle at slow speed.

It is available in four application versions. For 28-day cured concrete Horizontal (H) and Vertical (V) grade versions should be used. For Green Concrete (GC) Horizontal (GCH) and Vertical (GCV) grade versions are used. Polycoat-Aquaseal™ 5000 has VOC levels equal to or less than 100 grams per liter. Make sure to use the correct grade of product which complies with VOC regulations/requirements applicable as per federal, state, statutory, counties, cities and local bodies at the place of installation.

Color

Black

Coverage

The approximate coverage is 2 gallons/100 per sqft (0.41/ sqft) or 100 sqft/gallon which results in a dry film thickness of 28 mils (355 microns). Coverage rate will depend on surface roughness and porosity.

Surface Preparation

Refer to General Guidelines for complete information.

Joints, Cracks and Flashing:

Apply a stripe coat of Polycoat-Aquaseal™ 5000 over all cracks up to 1/16" (1.58 mm) width. All cracks over 1/16" (1.58 mm) width must be caulked with a polyurethane sealant.

All metal flashings must be primed with manufacturer's

Features

- Economical
- User Friendly
- Labor Saving
- Meets the Criteria of ASTM C836 and E96
- Resistant to Bacteria
- User Friendly

Typical Uses

- Basements
- Between Slabs
- Bridges
- Planters
- Shower Pans
- Tunnels

PACKAGING

5-Gallon 5 gallon (18.9 liter) pail

55-Gallon 55 gallon drum, net fill 50 gallons (189 liters)

recommended primer.

Mixing

Before application, Polycoat-Aquaseal™ 5000 should be thoroughly mixed using a mechanical mixer at slow speed to ensure a homogeneous material. Take care not to allow entrapment of air into the material. Do not mix in an up and down motion.

Application

Polycoat-Aquaseal™ 5000 may be applied with a brush, squeegee, trowel, roller or airless sprayer. Over smooth surfaces, such as poured-in-place concrete, apply Polycoat-

Technical Data (Based on Draw Down Film) Polycoat-Aquaseal™ 5000 (100 VOC) Properties

	5000H HORIZONTAL	5000V VERTICAL	5000GCH HORIZONTAL	5000GCV VERTICAL
Hardness, ASTM D2240	50 ± 5 Shore A	45 ± 5 Shore A	50 ± 5 Shore A	45 ± 5 Shore A
Tear Resistance, Die C, ASTM D624	70 ± 20 pli 9.3 ± 2.6 kN/m	100 ± 20 pli 13.3 ± 2 kN/m	70 ± 20 pli 9.3 ± 2.6 kN/m	100 ± 20 pli 13.3 ± 2 kN/m
Tensile Strength, ASTM D412	450 ± 50 psi 3.1 ± 0.3 MPa	500 ± 50 psi 3.4 ± 0.3 MPa	450 ± 50 psi 3.1 ± 0.3 MPa	500 ± 50 psi 3.4 ± 0.3 MPa
Ultimate Elongation, ASTM D412	500 ± 50%	500 ± 50%	450 ± 50%	450 ± 50%
Specific Gravity	1.28 ± 0.1	1.20 ± 0.3	1.28 ± 0.1	1.20 ± 0.1
Total Solids by Weight, ASTM D2369	95 ± 3%	91 ± 3%	95 ± 3%	91 ± 3%
Total Solids by Volume, ASTM D2697	94 ± 3%	89 ± 3%	94 ± 3%	89 ± 3%
Viscosity at 80°F (27°C)	5000 ± 2000 cps	40,000 ± 20,000 cps	5000 ± 2000 cps	40,000 ± 2000 cps
Volatile Organic Compounds, ASTM D-2369-81	0.83 lb/gal, 100 gm/liter	0.83 lb/gal, 100 gm/liter	0.83 lb/gal, 100 gm/liter	0.83 lb/gal, 100 gm/liter
Service Temperature	-25°F to 200°F -31.7°C to 65°C	-25°F to 200°F -31.7°C to 65°C	-25°F to 200°F -31.7°C to 65°C	-25°F to 200°F -31.7°C to 65°C

Aquaseal™ 5000 evenly in two 30 mil coats. Polycoat-Aquaseal™ 5000WC-H (Water Catalyzed) can be applied at any thickness.

A manufacturer approved reinforcing fabric may be applied into the wet coating if desired

Membrane Protection

As soon as possible after completion of a successful water test or visual inspection and/or repairs, cover membrane with approved protection board or geotextile drainage composite. All horizontal and vertical membrane must be protected.

Curing

At 75°F (24°C) and 50% relative humidity, allow each coat of Polycoat-Aquaseal™ 5000 Vertical, Horizontal and Green Concrete to cure 16 hours minimum.

Cure time will vary depending on temperature and humidity. If more than 48 hours pass between coats the surface must be re-primed.

Polycoat-Aquaseal™ 5000 is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in thickness of application. Limit single coat thickness to 30-40 wet mils (760-1016 microns).

Cleanup

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

Storage

Polycoat-Aquaseal™ 5000 has a shelf life of one year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Limitations

The following conditions must not be coated with Polycoat Products deck coating systems or products: on grade slabs, split slabs with buried membrane, sandwich slabs with insulation, slabs over unvented metal pan, swimming pools, magnesite, lightweight concrete. Asphalt surfaces and asphalt overlays may be coated with Polycoat coating systems if first coated with the Polycoat-Aquaseal™ 5000.

Surfaces must be dry, clean and free of foreign matter. Clear coating may turn opaque and cloudy due to moisture penetration, especially in exterior applications. Surface may be slippery when wet. Containers that have been opened must be used as soon as possible. Do not dilute under any circumstance.

With regard to coating asphalt surfaces, please contact Polycoat technical department.

May not be exposed to Ultraviolet rays.

Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2020 Polycoat Products. All rights reserved. Revision 20200914.DM

Warning

This product contains Aromatic Hydrocarbons, Isocyanates and Solvent.