



Product Description

Metal Primer 130 is a two component, liquid applied, urea polyurethane primer. Polycoat Products manufactures products in different VOCs ranging from 100 to 340 gms/liter to comply with VOC requirement in various regions. Make sure to use the correct grade of product which complies with VOC regulations/requirements applicable as per federal, state, statutory, counties, cities and local bodies at the place of installation. **This product is NOT for sale in California or any location where a VOC of 360 gms/liters is not acceptable.**

Features

- Low Odor
- Quick Drying

Typical Uses

- Glass Reinforced Plastics
- Metal
- Polyurethane Elastomeric Surfaces

Packaging

1-Gallon Kit	One - 1 quart can of Side-A Clear Liquid, net 0.25 gallon (0.95 liters) and Three - 1 quart cans of Side-B Off White Liquid, net 0.25 gallon (0.95 liters) each can
4-Gallon Kit	One - 1 gallon can of Side-A Clear Liquid, net 1 gallon (3.78 liters) and One - 5 gallon pail of Side-B Off-White Liquid, net 3 gallon (11.34 liters)

Color

Side-A: Clear, Side-B: Off-White

Coverage

The approximate coverage is 1 gallon/300 sqft (0.14 l/sqm). Coverage rate will depend on surface roughness and porosity.

Surface Preparation

Remove all contaminant, oil and grease from substrate. Refer to General Guidelines for complete information.

Mixing

Metal Primer 130 may not be diluted under any circumstance. The volume mixing ratio: 1 part Side-A to 3 parts Side-B (1A:3B). Metal Primer 130 Side-B should be thoroughly mixed prior to combining to ensure a homogeneous material. The

Technical Data (Based on Draw Down Film)

Coverage Rate	1 gal/300 sqft 0.14 l/sqm
Dry Film Thickness per Coat	3 ± 1 mils 76 ± 25 microns
Mixing Ratio by Volume	1A : 3B
Pot Life at 75°F (24°C), 50% RH	20-30 min
Hardness, ASTM D2240	70 ± 5 Shore D
Specific Gravity, Side-A	1.06 ± 0.1
Side-B	1.47 ± 0.1
Total Solids by Weight, ASTM D2369	75 ± 3%
Total Solids by Volume, ASTM D2697	62 ± 3%
Viscosity at 75°F (24°C) Side-A & Side B Combined	500 ± 200 cps 2500 ± 500 cps
Volatile Organic Compounds, ASTM D2369-81	3 lb/gal 360 gm/liters


combined components should be thoroughly mixed using a mechanical mixer at slow speed or for at least 5 minutes if mixed by hand. Do not mix in an up and down motion.

Application

Metal Primer 130 should be applied at the rate of 1 gallon/300 sqft (0.14 l/sqm) (mixture of Side-A & Side-B). It can be applied using an airless sprayer, brush, or phenolic resin core roller.

Allow Metal Primer 130 to become nearly tack free before applying the coating. Recommended surface temperature should be greater than 50°F (10°C). If Metal Primer 130 is allowed to dry completely, reprime the surface before proceeding.

Metal Primer 130 is very sensitive to heat and moisture. Higher



temperatures and/or high humidity will significantly accelerate the cure time and pot life. Use caution in batch sizes and thickness of application. Low temperature and/or low humidity will extend the cure time.

Cleanup

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

Storage

Metal Primer 130 has a shelf life of 1 year from date of manufacture in original, factory sealed containers. Side-A and Side-B must be stored between 60-95°F (15-35°C). **Avoid freezing temperatures.** Store containers on wooden pallets to avoid direct contact with the ground.

Limitations

Not UV stable. Cannot withstand direct wear or abrasion. Containers that have been opened must be used as soon as possible. Metal Primer 130 is difficult to clean up after it has cured. Mix no more material than can be used within 20 minutes.

This product is NOT for sale in California or any location where a VOC of 360 gms/liters is not acceptable.

Warning

This product contains Isocyanates.

Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2020 Polycoat Products. All rights reserved. Revision 20200915.DM